

Sand Dollar 2933

Azure 9021

Specifications

Contents

100% FR polyester

Weight

13.5 ± 1.0 oz./lin. yd.

Width

72" min. useable

Repeat

20.8" vertical, 18.9" horizontal

Treatment

Antimicrobial

Backing

none

Treatment

Antimicrobial

Cleaning Code

<p>Standard Care Label W-S. Commercial wash at 160°F maximum wash temperature using detergents recommended for the type of washing machines being used, no chlorine bleach. Rinse warm. Do not overload the washer as this may result in inadequate cleansing of the fabric and excessive wrinkling. Dry on synthetic (cool) setting until slightly damp or just dry. Do not overload the dryer. Over-drying or drying at hot temperatures may cause unacceptable shrinkage to occur. If necessary, press with a cool iron (“polyester” or “synthetics” setting, max temp 275° F). May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.</p>

Performance



Breaking Strength (ASTM D5034)

200 lbf min. warp and 100 lbf min. fill

Tear (ASTM D2261)

10 lbf min. warp and 10 lbf min. fill

Seam Slippage (ASTM D4034)

60 lbf min. warp and fill

Colorfastness to light (AATCC 16.3 Option 3)

Grade 4 min. at 60 hours

Colorfastness to crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet

Flammability

NFPA 701 TM#1 - Pass

Miscellaneous

Every effort has been made to ensure color accuracy of the digital images, however, please order a sample before specification. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric. Binder card not available. Pattern shown railoaded.

Proudly woven in North America supporting our local communities.

