Surf 2941

Outer Banks 9010

Specifications

Contents

100% FR polyester

Weight 13.4 ± 1.0 oz./lin. yd.

Width 72" min. useable

Repeat 35" vertical, 37.7" horizontal

Treatment Antimicrobial

Backing none

Treatment Antimicrobial

Cleaning Code

Standard Care Label W-S. Commercial wash at 160°F maximum wash temperature using detergents recommended for the type of washing machines being used, no chlorine bleach. Rinse warm. Do not overload the washer as this may result in inadequate cleansing of the fabric and excessive wrinkling. Dry on synthetic (cool) setting until slightly damp or just dry. Do not overload the dryer. Over-drying or drying at hot temperatures may cause unacceptable shrinkage to occur. If necessary, press with a cool iron ("polyester" or "synthetics" setting, max temp 275° F). May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Performance





Breaking Strength (ASTM D5034) 225 lbf min. warp and 100 lbf min. fill

Tear (ASTM D2261) 10 lbf min. warp and fill

Seam Slippage (ASTM D4034) 60 lbf min. warp and fill

Colorfastness to light (AATCC 16.3 Option 3) Grade 4 min. at 60 hours

Colorfastness to crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet

Flammability

CA Technical Bulletin 117-2013 Section 1

Miscellaneous

Every effort has been made to ensure color accuracy of the digital images, however, please order a sample before specification. Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric. Binder card not available. Pattern shown railroaded.

Proudly woven in North America supporting our local communities.



